

表 1(续)

| 牌号 | 包铝分类 | 供应状态 | 试样状态 | 厚度 ^a /mm | 抗拉强度 ^b R_m /MPa | 规定非比例 延伸强度 ^b $R_{p0.2}$ /MPa | 断后伸长率/% | | 弯曲 半径 ^d |
|--------------|------|--------------|------------|---------------------|---------------------------------|---|------------|--------------|-----------------------|
| | | | | | | | A_{50mm} | $A_{5.65}^c$ | |
| 不 小 于 | | | | | | | | | |
| 5005 | — | H12 | H12 | >0.20~0.50 | 125~165 | 95 | 2 | — | 0t |
| | | | | >0.50~1.50 | | | 2 | — | 0.5t |
| | | | | >1.50~3.00 | | | 4 | — | 1.0t |
| | | | | >3.00~6.00 | | | 5 | — | 1.0t |
| | | H14 | H14 | >0.20~0.50 | 145~185 | 120 | 2 | — | 0.5t |
| | | | | >0.50~1.50 | | | 2 | — | 1.0t |
| | | | | >1.50~3.00 | | | 3 | — | 1.0t |
| | | | | >3.00~6.00 | | | 4 | — | 2.0t |
| | | H16 | H16 | >0.20~0.50 | 165~205 | 145 | 1 | — | 1.0t |
| | | | | >0.50~1.50 | | | 2 | — | 1.5t |
| | | | | >1.50~3.00 | | | 3 | — | 2.0t |
| | | | | >3.00~4.00 | | | 3 | — | 2.5t |
| | | H18 | H18 | >0.20~0.50 | 185 | 165 | 1 | — | 1.5t |
| | | | | >0.50~1.50 | | | 2 | — | 2.5t |
| | | | | >1.50~3.00 | | | 2 | — | 3.0t |
| | | H22 H32 | H22 H32 | >0.20~0.50 | 125~165 | 80 | 4 | — | 0t |
| | | | | >0.50~1.50 | | | 5 | — | 0.5t |
| | | | | >1.50~3.00 | | | 6 | — | 1.0t |
| | | | | >3.00~6.00 | | | 8 | — | 1.0t |
| | | H24 H34 | H24 H34 | >0.20~0.50 | 145~185 | 110 | 3 | — | 0.5t |
| | | | | >0.50~1.50 | | | 4 | — | 1.0t |
| | | | | >1.50~3.00 | | | 5 | — | 1.0t |
| | | | | >3.00~6.00 | | | 6 | — | 2.0t |
| | | H26 H36 | H26 H36 | >0.20~0.50 | 165~205 | 135 | 2 | — | 1.0t |
| | | | | >0.50~1.50 | | | 3 | — | 1.5t |
| | | | | >1.50~3.00 | | | 4 | — | 2.0t |
| | | | | >3.00~4.00 | | | 4 | — | 2.5t |
| | | H28 H38 | H28 H38 | >0.20~0.50 | 185 | 160 | 1 | — | 1.5t |
| | | | | >0.50~1.50 | | | 2 | — | 2.5t |
| | | | | >1.50~3.00 | | | 3 | — | 3.0t |
| | | H112 | H112 | >6.00~12.50 | 115 | — | 8 | — | — |
| | | | | >12.50~40.00 | 105 | | — | 10 | — |
| >40.00~80.00 | 100 | | | — | 16 | | — | | |
| F | — | >2.50~150.00 | — | — | — | — | — | | |

